

LS 26500plus

Primary Li-SOCl₂ cell

High energy density 3.6 V C-size bobbin cell

Saft's LS 26500plus cell is ideally suited for long-term applications (typically from 5 to 20+ years), featuring low base currents and periodic pulses.

Benefits

- High capacity and high energy (1175 Wh/l and 637 Wh/kg)
- High voltage response, stable during most of the lifetime of the application
- Wide operating temperature range (-60°C / + 85°C)
- Low self-discharge compatible with long operating life (less than 1% after 1 year of storage at + 20°C)
- Superior resistance to corrosion
- Low magnetic signature

Key features

- Bobbin construction
- Well controlled passivation
- Hermetic construction with glass-to-metal seal
- Stainless steel can
- Non-flammable electrolyte
- RoHS and REACH compliance
- Made in France

Designed to meet all major quality, safety and environment standards

- Safety: UL 1642, IEC 60086-4
- ATEX: IEC 60079-11 part 10.5 (T4 temperature rating at + 60°C)
- Transport: UN 3090 and UN 3091
- Quality: ISO 9001, Saft Excellence System, continuous program
- CE: P/N: 06415Z

Typical Applications

- Utility Metering
- Internet of Things
- Alarms and security
- Medical devices
- Tracking systems
- Professional electronics



Electrical characteristics¹

Nominal capacity (under 4 mA, +20°C, 2.0 V cut-off) ³	8.5 Ah
Open circuit voltage (at +20°C)	3.67 V
Nominal voltage (under 0.5 mA, + 20°C)	3.6 V
Nominal energy	30.6 Wh
Pulse capability ⁴	Up to 300 mA
Maximum recommended continuous current ⁷	150 mA

For battery sizing, consult Saft

Operating conditions

Operating temperature range ⁵	-60°C / +85°C (-76°F / +185°F)
Storage temperatures (max recommended) ⁶	+30°C (+86°F)

Physical characteristics²

Diameter (max)	26.0 mm (1.02 in)
Height (max)	50.4 mm (1.97 in)
Typical weight	47 g (1.65 oz)
Li metal content	approx. 2.2 g

Customized cell connections

CN, CNR	Radial tabs
2 PF, 3 PF, 3 PF RP, 4 PF	Radial pins
CNA	Axial leads
GCJ	Connector

Other configurations upon request

¹Typical values relative to cells stored up to one year at + 30°C max.

²Sleeved cell.

³Dependent upon current drain, temperature, cut-off and cell orientation.

⁴Under 300 mA / 0.1 second pulses, drained every 2 minutes at + 20°C from undischarged cells during 24 h, with 10 µA base current, yield voltage readings above 3.0 V after initial stabilisation. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions or for high pulse currents. Consult Saft.


⁵Operation above ambient temperature may lead to reduced capacity and lower voltage readings. Consult Saft.

⁶For more severe conditions, consult Saft.


⁷If above this value, please consult Saft.

LS 26500plus

Primary Li-SOCl₂ cell



Finished version with protruding positive end cap



Finished version with flat positive end cap




Dimensions in mm

Storage

- The storage area should be clean, cool (preferably not exceeding +30°C), dry and ventilated.

Warning

- Fire, explosion and burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell (use tabbed cell versions instead).
- Do not remove the cells from their original packing before use.
- Do not store the cells in bulk to avoid accidental short circuiting.
- Do not mix new and used cells or cells from different origins.
- Mind the polarities of the cell.



The curves presented are based on experimental averages and do not necessarily reflect the minimum values that may be observed, particularly when the discharge regime exceeds the nominal conditions specific to each temperature.

26, quai Charles Pasqua
92300 Levallois-Perret - France
www.saft.com

Saft, a subsidiary of TotalEnergies
S.A.S. au capital de 26 724 876 €
R.C.S. Nanterre 481 480 465

Document N° 31029-2-0426
Edition: April 2026

Data in this document is subject to change without notice and becomes contractual only after written confirmation.
Photo credits: © Saft